

Product Information

Product Description

Ti-Pure[™] R-104 is a rutile titanium dioxide pigment manufactured by the chloride process. It is specifically designed to give outstanding melt flow with highly loaded thermoplastics masterbatches. Ti-Pure R-104 combines high tinting strength and blue undertone. Ti-Pure R-104 offers excellent lacing resistance in high-temperature extrusion coating and cast film applications. Ti-Pure R-104 is supplied as a fine, dry, white powder with the following general properties.

Table 1. Physical Properties

Titanium Dioxide, wt%, min.	97
Alumina, wt%, max.	1.7
Organic Treatment, wt%, carbon	0.3
Specific Gravity	4.2

Suggestions for Use

Ti-Pure[™] R-104 is designed primarily for plastic applications. The properties of Ti-Pure [™] R-104 are especially valuable where high concentrations of pigment are desired in thermoplastic masterbatches and where minimal effect is desired on melt flow. This, combined with the following, makes Ti-Pure [™] R-104 a valuable asset to the color formulator.

Figure 1. Optical Properties




Table 2. General Properties

Opacity Strength	High		
Undertone Tint	Very Blue		
Dispersibility in:			
Thermoplastics	Excellent		
Dry Blending Operations	Excellent		
Effect on Melt Flow	Minimal		
Lacing Resistance	Excellent		
Weathering Resistance	"Chalking" grade in PVC use		



Ti-Pure™ R-104 Titanium Dioxide


Ti-Pure[™] R-104 has a unique surface treatment that causes it to have minimal effect on the melt flow properties of masterbatches. This allows the masterbatch producer to achieve high loadings in relatively low melt index resins and still have a melt processible material. The effects of Ti-Pure ™ R-104 and Ti-Pure ™ R-101 on melt index are shown in **Table 3**.

Table 3. Melt Index

Melt Index Effects in Three Resins					
Pigment	wt%	12	22	70	
R-101	50	7.4	_	_	
R-104	50	9.3	_	_	
R-101	60	4.0	_	_	
R-104	60	8.1	_	_	
R-101	70	nil	nil	_	
R-104	70	5.4	10.2	_	
R-101	80	_	_	nil	
R-104	80	_	_	10.6	


While melt index is a good measure of relative performance, the method does not reveal much about actual process conditions. Capillary melt flow measurements fill this gap, allowing viscosity to be measured over the normal range of processing equipment. Figure 2 shows the profound reduction in viscosity that can be achieved with Ti-Pure* R-104 in a 70% low density polyethylene masterbatch.

Figure 2. Melt Rheology of 70% TiO₂ Masterbatch (12 MFI LDPE at 190 °C)



Ti-Pure[™] R-104 easily "wets" with the surface of the thermoplastics and can dramatically increase process rates during preparation of thermoplastic masterbatches in certain types of compounding equipment. A typical internal mixer power curve is shown in **Figure 3**, which compares Ti-Pure[™] R-104 and Ti-Pure[™] R-101 grades of titanium dioxide. It is apparent that cycle time reductions of up to 25% can be readily achieved.

Figure 3. Internal Mixer Power Curve (R-104 versus R-101 Standard)



Shipping Containers

Ti-Pure[™] R-104 rutile titanium dioxide is available in two recyclable package types to meet your needs:

- 25 kg polyethylene bags
- 1 metric ton (1,000 kg) flexible intermediate bulk containers

For further information about this grade or to request a sample, please see the Ti-Pure[™] web site.

Ti-Pure™ R-104 Titanium Dioxide

CAUTION: Do not use Chemours materials in medical applications involving permanent implantation in the human body or contact with bodily fluids or tissues, unless the material has been provided from Chemours under a written contract that is consistent with Chemours policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your Chemours representative. You may also visit www.teflon.com/industrial to download a copy of the "Chemours POLICY Regarding Medical Applications" C-00000 and "Chemours CAUTION Regarding Medical Applications" C-00000. For medical emergencies, spills, or other critical situations, call (800) 441-7515 within the United States. For those outside of the United States, call (302) 774-1000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit www.titanium.chemours.com

© 2015 The Chemours Company TT, LLC. Ti-Pure and any associated logos are trademarks or copyrights of The Chemours Company TT, LLC. Chemours and the Chemours Logo are trademarks of The Chemours Company

Replaces H-52206-7 C-10423 (7/15)